

# PRODUCT DATA

## RUST VETO 344

A black, liquid rust preventive, which contains a volatile solvent. Shortly after application the solvent will evaporate to leave a black film which, while it is dry to the touch, will remain soft enough to expand or contract with the coated surfaces without cracking, chipping or flaking off.

### INTENDED USES:

**RUST VETO 344** is intended for the long term preservation of ferrous or non-ferrous metal parts which are to be stored indoors or outdoors, without wrapping, under the most severe climatic conditions.

### METHODS OF APPLICATION:

**RUST VETO 344** can be applied neat by brushing, dipping or spraying at room temperature. The product may be diluted with Stoddards Solvent for ease of spraying. When the product is applied as a dilution it is advisable to apply 2 coats and to allow the first to dry for 12 hours before the second is applied.

### TYPICAL PHYSICAL PROPERTIES:

Appearance of product	Black Liquid
API Gravity @ 16°C	28.9
Flash Point (Minimum) (C.O.C.)	40°C
Pour Point	-6°C
Specific Gravity	1.056
Coverage	100 ft <sup>2</sup> /Litre
Drying time (dust free)	4 hours
Film thickness (approximate by dipping)	0.08 mm



**HOUGHTON CANADA INC.**  
P.O. Box 113, Station "D"  
100 Symes Rd.  
Toronto, Ontario M6P 3J5  
Ph (416) 763-4691 • Fx (416) 763-3167